



TEST REPORT

Report No. :W2024-02510E-B

Date: April 11, 2024

Applicant name : CHANGZHOU CHANGYI EXHIBITION TENT CO.,LTD.

Applicant address : NO.308 XIA' AN,YAOGUAN,CHANGZHOU,JIANGSU

Contact person : /

Sample description : The following sample(s) was/were submitted and identified on behalf of the client as

Item name : PVC TARPAULIN

Colour : WHITE

Style No. : JFS201-1

Order No. : /

Composition : /

Other information : MANUFACTURER:ZHEJIANG JINDA;WEIGHT:850G/m²;DENSITY:1000*1000
9*9/cm;THICKNESS:0.68mm

Date received : March 25, 2024

Test completed : April 9, 2024

Remark : This test report supersedes our previous test report No. W2024-02510E-A which is hereby
deemed null and void.

Test details : Refer to the test details requested by the applicant on next page(s).



Approved by

Verified by

Prepared by

Zhejiang ZTT Testing Co.,Ltd.

Add.: No. 18, 2nd Jingdu Rd. , Zhejiang Haining Warp Knitting Industrial Zone, Zhejiang, China.
Tel.: 86-573-87989122 Fax.: 86-573-87989121 Http: // www.zttcn.com



TEST REPORT

Report No. : W2024-02510E-B

Date: April 11,2024

Fire behaviour(Method: DIN 4102-1:1998)**Conditioning**

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of 23 ± 2 °C, and a relative humidity of 50 ± 6 %.

Test results

“Brandschacht” Test according to DIN 4102-1:1998

Exposed surface: The Front face

Results of “Brandschacht” Test (part 1)						
Line No.		Unit	Test Line assemblies No.			
			A	B	C	D
1	Specimen fixings according to DIN 4102 part15,table	-	1			
2	Max. flame height above lower sample edge;	cm	30			
3	Time ¹⁾	s	1			
4	<u>Melting/burning through</u> Time ¹⁾	s	1			
5	<u>Back of specimen</u> Flaming/glowing, Time ¹⁾	s	1			
6	Discolouring, Time ¹⁾	s	1			
7	<u>Burning droplets</u> Begin 1) Amount	s	No / /			
8	Specimen material falling off in separate droplets		/			
9	Specimen material falling off continuously		/			
10	<u>Burning parts</u> Begin 1)	s	No /			
11	Parts of sample falling off separately		/			
12	Parts of sample falling off continuously		/			
13	Duration of continued combustion on mesh base (max.)	s	No			
14	<u>Burner flame impairment by dripping/falling material</u> Time ¹⁾	s	No /			
	<u>Premature ending of test</u>		/			
15	End of burning at specimen ¹⁾	s	/			
16	Time when test terminated (if applicable) ¹⁾	s	/			
	<u>Burning after end of test</u>		NO			
17	Duration	s	/			
18	Number of specimens		/			
19	Front of specimen		/			
20	Back of specimen		/			
21	Height of flame	cm	/			

Zhejiang ZTT Testing Co.,Ltd.

Add.: No. 18, 2nd Jingdu Rd. , Zhejiang Haining Warp Knitting Industrial Zone, Zhejiang, China.
Tel.: 86-573-87989122 Fax.: 86-573-87989121 Http: // www.zttcn.com



TEST REPORT

Report No. : W2024-02510E-B

Date: April 11,2024

Results of "Brandschacht" Test (part 2)						
Line No.		Unit	Test Line assemblies No.			
			A	B	C	D
	<u>Glowing after end of test</u>		No			
22	Duration	s	/			
23	Number of specimens		/			
24	Front of specimen		/			
25	Back of specimen		/			
26	Top half of specimen		/			
27	Bottom half of specimen		/			
	<u>Residual length</u>					
28	Single results	cm	67 58	59 56		
29	Average of the single results	cm	60			
30	<u>Smoke temperature</u>	°C	147			
31	Max. of average Time ¹⁾	s	180			

Note: 1)time from start of testing

2) Normal Flammability Test according to DIN 4102-1 Clause 6.2

Flame application: bottom edge ignition

Specimen No.		1	2	3	4	5
Reaching the measuring mark within 20 seconds	Warp	No	No	No	No	No
	Weft	No	No	No	No	No

Flame application: surface ignition

Specimen No.		1	2	3	4	5
Reaching the measuring mark within 20 seconds	Warp	No	No	No	No	No
	Weft	No	No	No	No	No

All timings are from start of testing

Criteria for classification for Class B1 (DIN 4102-1 Clause 6.1.2)

All materials, except flooring, may be classed as B1 materials if they met,

a) Pass DIN 4102-16 "brandschacht" test if

1) The mean value for the residual length of each specimen is at least 15 cm, and no individual values are lower than 0 cm;

2) The mean effluent temperature does not exceed 200°C in any test;

3) The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.

b) Pass DIN 4102-1 Clause 6.2.3 Ignitability Test if,

For each specimen, flaming doesn't reach the gage mark within 20s after flame application.

Zhejiang ZTT Testing Co.,Ltd.

Add.: No. 18, 2nd Jingdu Rd. , Zhejiang Haining Warp Knitting Industrial Zone, Zhejiang, China.

Tel.: 86-573-87989122 Fax.: 86-573-87989121 Http: // www.zttcn.com



TEST REPORT

Report No. : W2024-02510E-B

Date: April 11,2024

Conclusion:

The tested sample meets the low flammability requirements of class B1 of building materials under DIN 4102-1:1998.

STATEMENTS:

This test report does not replace any mandatory certification of the product that may be required.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

Remark: This item is only approved by CNAS.

Zhejiang ZTT Testing Co.,Ltd.

Add.: No. 18, 2nd Jingdu Rd. , Zhejiang Haining Warp Knitting Industrial Zone, Zhejiang, China.
Tel.: 86-573-87989122 Fax.: 86-573-87989121 Http: // www.zttcn.com



TEST REPORT

Report No.: W2024-02510E-B

Date: April 11, 2024

Sample Photo



***** End of Report *****

Zhejiang ZTT Testing Co.,Ltd.

Add.: No. 18, 2nd Jingdu Rd. , Zhejiang Haining Warp Knitting Industrial Zone, Zhejiang, China.
Tel.: 86-573-87989122 Fax.: 86-573-87989121 Http: // www.zttcn.com